



Kuwait Chemical Manufacturing Company KSC

الشركة الكويتية للتصنيع الكيماوي (ش.م.ك.)

TECHNICAL DATA SHEET

01 June 2005

LONG OIL ALKYD

KULAC LSN 40W/58

Kulac LSN 40W/58 is a pumpable, 58% solids, long oil alkyd in white spirits. **Kulac LSN 40W/58** has been formulated for use in high quality architectural coatings when diluted with suitable solvents.

Application Areas

Kulac LSN 40W/58 may be used in the formulation of brush or roller applied decorative finishes such as:

- Enamels
- Undercoats
- Primers

Physical Characteristics

Parameter	Units	Limits
Oil Length	%	± 62
Oil Type	Nil	Linoleic Rich
Non-Volatile Content	%	58 ± 2
Viscosity (25°C)	Poise	13 - 17
Viscosity (25°C)	Gardner	X - Y
Solids @ 2 Poise in W.S.	%	± 48
Acid Value (on solids)	mg KOH/g	10 Max.
Colour	Gardner	4 Max.
Clarity	Nil	Clear
B. K. Drying Times ¹		
Touch Dry	Hours	± 2
Hard Dry	Hours	± 3 ½

Compatibility Characteristics ²

Solvents	
Alcohols	Limited
Aliphatics	Compatible
Aromatics	Compatible
Esters	Compatible
Ketones	Compatible
Other Film Formers	
Amino Resins	Incompatible
Bodied Oils	Limited
Chlorinated Rubber	Limited
Drying Oils	Compatible
Long Oil Alkyds	Compatible
Medium Oil Alkyds	Compatible

Note:

¹ Sample containing 0.05% Co and 0.5% Pb on resin solids reduced to 100 seconds Ford 4 with white spirits and matured for 48 hours. The varnish is subsequently applied at a 75µ wet film thickness to glass panels and allowed to dry under laboratory conditions.

² Compatibility characteristics are provided for guidelines only. Combinations should be thoroughly checked before use.

Packaging

Kulac LSN 40W/58 is available in 1000 Kg Net IBCs or road tankers (approximately 18 tons). For alternative packaging requirements please contact our Sales Department.

Variants

Kulac LSN 40W/58 is also available as a 100% solids resin version, **LSN 40N/100**, an 80% solids version, **LSN 40W/80** and a 70% solids version, **Kulac LSN 40W/58**. White spirits is the base solvent in all diluted versions.

Storage Stability and Safety

Kulac alkyd resins should be stored below 30°C in a cool, dry position away from direct sunlight or other heat sources. Under these conditions the resins will have a shelf life of one year.

Kulac alkyds should additionally be stored and handled in accordance with local statutory regulations.

Address P. O. Box 26011, Safat, Kuwait, 13121

Telephone (+65) 326-3297 or 326-3497

Fax (+65) 326-0179

Document Revision Number

A-01

E-Mail sales@kcmckw.com

No warranty or guarantee, express or implied, is made regarding the performance or stability of any product since the manner of use and/or conditions of storage are beyond our control. Additionally, KCMC are committed to improving all aspects of our product range through continued research and development. As such product composition and/or specifications may change without notice.