



# Kuwait Chemical Manufacturing Company KSC

الشركة الكويتية للتصنيع الكيماوي (ش.م.ك.)

## TECHNICAL DATA SHEET

31 August 2005

**LONG OIL ALKYD**

**KULAC LSN 52W/58**

**Kulac LSN 52W/58** is a 58% solids long oil alkyd in white spirits formulated for use in quality architectural coatings exhibiting good gloss, durability and yellowing resistance.

### Application Areas

**Kulac LSN 52W/58** may be used in the formulation of brush or roller applied decorative finishes such as:

- Enamels
- Undercoats
- Primers

### Physical Characteristics

Parameter	Units	Limits
Oil Length	%	± 58
Oil Type	Nil	Linoleic Rich
Non-Volatile Content	%	58 ± 2
Viscosity (25°C)	Poise	± 60
Viscosity (25°C)	Gardner	± Z4
Viscosity (25°C) @ 55% solids	Gardner	Z to Z <sub>2</sub>
Solids @ 2 Poise in W.S.	%	± 44
Acid Value (on solids)	mg KOH/g	10 Max.
Colour	Gardner	5 Max.
Clarity	Nil	Clear
<b>B. K. Drying Times <sup>1</sup></b>		
Touch Dry	Hours	± 2
Hard Dry	Hours	± 3 ½

### Compatibility Characteristics <sup>2</sup>

Solvents	Compatibility
Alcohols	Limited
Aliphatics	Compatible
Aromatics	Compatible
Esters	Compatible
Ketones	Compatible
<b>Other Film Formers</b>	
Amino Resins	Incompatible
Bodied Oils	Limited
Chlorinated Rubber	Limited
Drying Oils	Compatible
Long Oil Alkyds	Compatible
Medium Oil Alkyds	Compatible

### Note:

<sup>1</sup> Sample containing 0.05% Co and 0.5% Pb on resin solids reduced to 100 seconds Ford 4 with white spirits and matured for 48 hours. The varnish is subsequently applied at a 75µ wet film thickness to glass panels and allowed to dry under laboratory conditions.

<sup>2</sup> Compatibility characteristics are provided for guidelines only. Combinations should be thoroughly checked before use.

### Packaging

**Kulac LSN 52W/58** is available in 190 Kg Net mild steel tight head drums or road tankers of approximately 18 tons. For alternative packaging requirements please contact our Sales Department.

### Variants

**Kulac LSN 52W/58** is also available as a 70% solids variant, **Kulac LSN 52W/70**.

### Storage Stability and Safety

Kulac alkyd resins should be stored below 30°C in a cool, dry position away from direct sunlight or other heat sources. Under these conditions the resins will have a shelf life of one year.

Kulac alkyds should additionally be stored and handled in accordance with local statutory regulations.

**Address** P. O. Box 26011, Safat, Kuwait, 13121

**Telephone** (+65) 326-3297 or 326-3497

**Fax** (+65) 326-0179

**Document Revision Number**

A-01

**E-Mail** sales@kcmckw.com

No warranty or guarantee, express or implied, is made regarding the performance or stability of any product since the manner of use and/or conditions of storage are beyond our control. Additionally, KCMC are committed to improving all aspects of our product range through continued research and development. As such product composition and/or specifications may change without notice.