



# Kuwait Chemical Manufacturing Company KSC

الشركة الكويتية للتصنيع الكيماوي (ش.م.ك.)

## TECHNICAL DATA SHEET

04 November 2008

*Urethane Alkyd*

*KULAC LSU 19W/55*

**Kulac LSU 19W/55** is a 55% solids Urethaned Alkyd in white spirits specifically formulated for use in quality architectural coatings. **Kulac LSU 19W/55** exhibits excellent hardness, moisture resistance and durability.

### Application Areas

**Kulac LSU 19W/55** is generally used in the following decorative finishes:

- Varnishes and enamels for wooden flooring, mouldings, furniture and doors.
- Enamels for concrete flooring (e.g. show room and factory floors).
- Plaster primers and wall coatings for damp and high traffic areas such as bathrooms/kitchens.
- Metal primers with good salt spray resistance.
- **Kulac LSU 19W/55** is not recommended for exterior applications subjected to direct sunlight.

### Physical Characteristics

Parameter	Units	Limits
Oil Length <sup>3</sup>	%	± 64
Oil Type <sup>3</sup>	Nil	Linoleic Rich
Non-Volatile Content	%	55 ± 2
Viscosity (25°C) <sup>3</sup>	Poise	6 - 12
Viscosity (25°C)	Gardner	U - X
Solids @ 2 Poise in W.S. <sup>3</sup>	%	TBA
Acid Value (on solids)	mg KOH/g	5 Max.
Colour	Gardner	5 Max.
Clarity	Nil	Clear
Density @ 25°C <sup>3</sup>	g/cm <sup>3</sup>	± 0.908

### B. K. Drying Times<sup>1,3</sup>

Touch Dry	Hours	± 1
Hard Dry	Hours	± 3

### Compatibility Characteristics<sup>2</sup>

#### Solvents<sup>3</sup>

Alcohols	Limited
Aliphatics	Compatible
Aromatics	Compatible
Esters	Compatible
Ketones	Compatible

#### Other Film Formers<sup>3</sup>

Bodied Oils	Limited
Chlorinated Rubber	Limited
Drying Oils	Compatible
Long Oil Alkyds	Compatible
Medium Oil Alkyds	Compatible

### Note:

<sup>1</sup> Sample containing 0.05% Co and 0.5% Pb on resin solids reduced to 100 seconds Ford 4 with white spirits and matured for 48 hours. The varnish is subsequently applied at a 75µ wet film thickness to glass panels and allowed to dry under laboratory conditions.

<sup>2</sup> Compatibility characteristics are provided for guidelines only. Combinations should be thoroughly checked before use.

<sup>3</sup> These parameters are provided for indication only and do not form part of the product specification.

### Packaging

**Kulac LSU 19W/55** is available in 190 Kg Net mild steel tight head drums. For alternative packaging requirements please contact our Sales Department.

**Variants - Nil**

### Storage Stability and Safety

Kulac alkyd resins should be stored below 30°C in a cool, dry position away from direct sunlight or other heat sources. Under these conditions the resins will have a shelf life of one year.

Kulac alkyds should additionally be stored and handled in accordance with local statutory regulations.

**Address** P. O. Box 26011, Safat, Kuwait, 13121

**Telephone** (+65) 326-3297 or 326-3497

**Document Revision Number**

LSU 19W/55 A-01

**Fax** (+65) 326-0179 **E-Mail**

sales@uopkt.com

No warranty or guarantee, express or implied, is made regarding the performance or stability of any product since the manner of use and/or conditions of storage are beyond our control. Additionally, KCMC are committed to improving all aspects of our product range through continued research and development. As such product composition and/or specifications may change without notice.