



Kuwait Chemical Manufacturing Company KSC

الشركة الكويتية للتصنيع الكيماوي (ش.م.ك.)

TECHNICAL DATA SHEET

14 November 2005

GENERAL PURPOSE POLYESTER RESIN

KUPOL LR 1303

Kupol LR 1303 is a versatile, pre-accelerated, non-thixotropic, rapid curing unsaturated polyester based on orthophthalic anhydride and specifically designed for use in tropical climates. **Kupol LR 1303** has good mechanical and weathering properties.

Physical Characteristics

Curing Characteristics

Parameter	Units	Limits	Parameter	Units	Limits
Non-Volatile Content	%	58 ± 2%	Gel Time @ 25°C	Minutes	5 - 10
Acid Value (as supplied)	mg KOH/g	25 max.	Cure Time	Minutes	10 - 20
Viscosity (25°C)	cPs	200 - 250	Peak Exotherm	°C	± 180

Curing parameters are determined on a 100 gram sample stabilised at 25°C and catalysed 2% Methyl Ethyl Ketone Peroxide (50%).

Application Properties

Kupol LR 1303 has been formulated for use in hand or spray lay-up contact moulding applications, where mould drainage is not problematic, or in resin injection systems.

Suggested areas of Utilisation

Kupol LR 1303 may be used in any general purpose GRP application where it is resilience and impact strength are of benefit. **Kupol LR 1303** also has a fairly low exotherm which enables it to be used in multi-laminate systems where laminates are applied wet on wet. Examples of usage include, but are not limited to, water tanks, boat hulls (fresh water), kiosks and general jobbing. **Kupol LR 1303** should not be used in any applications requiring a high degree of structural stability and mechanical strength.

Curing

Kupol LR 1303 is pre-accelerated and requires only the addition of a suitable peroxide catalyst, such as MEKP to affect curing.

Although the product will cure with only a 0.5% addition of peroxide, a level of between 1 and 2 % is recommended to achieve optimal mechanical properties.

Post Curing

Kupol LR 1303 laminates should be post cured where the optimal mechanical properties are required and/or the product comes into contact with potable water or foodstuffs.

Packaging

Kupol LR 1303 is available in 220 Kg net mild steel tight head drums. For local deliveries , **Kupol LR 1303** is also available in 1400 and/or 1500 Kg stainless steel totes.

Storage Stability and Safety

Kupol LR 1303 is stable for a period of 6 months when stored in it's original container out of direct sunlight at temperatures not exceeding 25°C. This product contains styrene monomer and requires special care in handling. Please refer to the MSDS and any local statutory requirements.

Address P. O. Box 26011, Safat, Kuwait, 13121

Telephone (+65) 326-3297 or 326-3497

Document Revision Number

LR 1303 A-01

Fax (+65) 326-0179

E-Mail

sales@kcmckw.com

No warranty or guarantee, express or implied, is made regarding the performance or stability of any product since the manner of use and/or conditions of storage are beyond our control. Additionally, KCMC are committed to improving all aspects of our product range through continued research and development. As such product composition and/or specifications may change without notice.